

US EPA ARCHIVE DOCUMENT

## **EPA Disclaimer**

**Notice:** This document has been provided as part of the U.S. Environmental Protection Agency Sustainable Materials Management Web Academy (formally RCC) Recycling and Solid Waste Management Educational Series. This document does not constitute EPA policy or guidance and should not be interpreted as providing regulatory interpretations. Inclusion within this document of trade names, company names, products, technologies and approaches does not constitute or imply endorsement or recommendation by EPA. Information contained within this document from non-EPA presenters has not been screened or verified. Therefore, EPA has not confirmed the accuracy or legal adequacy of any information provided by the non-EPA presenters and used by EPA on this web site. Finally, links to non-EPA websites are provided for the convenience of the user; reference to these sites does not imply any official EPA endorsement of the opinions, ideas, data or products presented at those locations nor does it guarantee the accuracy of the information provided.

# Developing Trends in Rubberized Asphalt

U.S. EPA SMM Web  
Academy Webinar  
Series

February 21, 2013




Doug Carlson  
VP Asphalt Products



# Dramatic Increase in Cost

## Rubber Costs Less

### Crude Oil, Gas and Asphalt Costs



Recycled Materials Have To Perform  
Better, Save Money, and be  
Sustainable





**SAVE : MONEY**

# **Three Ways To Save With Rubber**

## **1. Reduce Thickness**

Asphalt-Rubber

18-22% Rubber Content

## **2. Substitute Virgin Polymers**

Rubberized Asphalt

8-12% Rubber Content

## **3. Less Maintenance Over Time**

Asphalt-Rubber, Hot Mix and Chip Seals



**SAVE : MONEY**

## 1. Reduce Thickness

City of Hemet, CA Design Alternatives	Design	Cost	Savings from Rubberized Asphalt Option
<b>Conventional Option A</b> (not feasible due to curb and gutter)	135 mm (5.3 in) conventional asphalt overlay	\$363,000	<b>\$124,000*</b>
<b>Conventional Option B</b> (reconstruction)	90 mm (3.5 in) conventional asphalt over 330 (13 in) mm Class 2 aggregate base	\$646,000	<b>\$382,000*</b>

***\*Rubberized Asphalt Option -  
39 mm (1.5 in) A-R HMA over 48 mm (2 in) conventional HMA.***



**SAVE : MONEY**


## 2. Substitute Virgin Polymers

Cost of Components	Neat	Polymer	ASTM A-R	PG Rubber
Neat Content in Binder	100%	97%	80%	88%
Rubber/Polymer Content in Binder	0%	3%	20%	10%
Additive				2%
Neat Cost	\$550	\$533	\$440	\$484
Rubber or Polymer Cost		\$108	\$80	\$40
Additive Cost				\$1.6
<b>Binder Material Cost/Ton</b>	<b>\$550</b>	<b>\$642</b>	<b>\$520</b>	<b>\$526</b>



**SAVE : MONEY**

### 3. Less Maintenance Over Time





# Common Gradations for Rubberized Asphalt

<b>Sieve size</b>	<b>Field Blend – Asphalt Rubber</b>	<b>Terminal or Field Blend- Rubberized Asphalt</b>
	<b>% Passing</b>	<b>% Passing</b>
<b>2.36-mm (#8)</b>	<b>100</b>	<b>100</b>
<b>2.00-mm (#10)</b>	<b>100</b>	<b>100</b>
<b>1.18-mm (#16)</b>	<b>75-95</b>	<b>100</b>
<b>600-<math>\mu</math>m (#30)</b>	<b>30-60</b>	<b>90-100</b>
<b>300-<math>\mu</math>m (#50)</b>	<b>5-30</b>	<b>&gt;20</b>
<b>150-<math>\mu</math>m (#100)</b>	<b>-</b>	<b>-</b>
<b>75-<math>\mu</math>m (#200)</b>	<b>0-5</b>	<b>-</b>



# Evaluation of Ground Tire Rubber in Asphalt Binders and Mixtures







# NCAT PG Results

Rubber Product	Dosage Rate, %	True Grade	Performance Grade
-30 Liberty	10%	80.7 – 23.6	76 – 22
-20 Liberty	10%	83.1 – 24.6	82 – 22
-20 Liberty	15%	87.9 – 21.3	82 – 16
Crackermill	10%	82.8 – 23.1	82 – 22
Cryo-Hammer	10%	82.2 – 23.2	82 – 22
Cryo-Hammer	15%	86.7 – 19.3	82 – 16
-30 Liberty Fines	10%	79.8 – 20.4	76 – 16
-16 Powderizers (1mm gap)	10%	76.3 – 21.8	76 – 16
-16 Powderizers (2 mm gap)	10%	84.7 – 21.8	82 – 16
Virgin Binder		69.2 – 24.7	67 - 22



## RTR Alternative Modifier

- About 3 x RTR loading is needed compared to SBS for similar properties.
  - Example: 3% SBS content = 9% RTR Content
- Suppose SBS costs \$2.00/Pound and RTR Costs \$0.50/Pound
  - Example:
  - 3 Pounds SBS = \$6.00,
  - 9 Pounds RTR = \$4.50
- Project with 1000 Tons of Modified of Binder
  - SBS at 3% = 30 Tons Needed @ \$2.00 = \$120,000
  - RTR at 9% = 90 Tons Needed @ \$0.50 = \$90,000



**Tire Rubber Performs In A Wider Range Of Temperatures than Asphalt**






## Performance Grade of Tire Rubber



- 140 C Softens and losses strength
- -70 C Glass transition
  - A PG 140-70?

# Interaction Between Asphalt and RTR








## A Change in Acceptance Testing

- In 2008, a substantial price spike in asphalt costs struck the paving industry nationwide.
- The use of Reclaimed Asphalt Pavement and Recycled Asphalt Shingles increased to solve the problem of high asphalt costs.
- The performance of RAP and RAS is measured through mix tests, not the liquid binder.
- This is a significant opportunity for Recycled Tire Rubber, as long as it costs less than asphalt and does not increase the liquid requirement (add cost) at the asphalt mix plant.



## New “Dry Process”

- Research Published at the LTRC, (Sam Cooper and Louay Mohammad), work underway at several Universities and with-in suppliers to the asphalt industry
- Rubber particles pre-treated with useful liquids before packaging, or co-packaged with low melt processing aids or powders before delivery to mix plant
- GA DOT using a co-packaged “Plant Mix” rubber





# Mix Performance Tests Are More Common with the Use of RAP and RAS







# Test Section in Hawkinsville, GA on SR 26







# RTR Blended with Reactive Type of Polymer








# Blended RTR Being Added To Plant at RAP Collar



## PELLETIZED ASPHALT-RUBBER



ASPHALTITE COVERING

HYDRATED LIME

## PelletPAVE™

Providing Asphalt-Rubber Technology  
for Pavement Maintenance



Cost Effective and Convenient







# Draindown Test for SMA & PFC








## RTR for Polymer Mixes Work Well in Porous Asphalt




**Video Courtesy of  
Seneca Petroleum Co  
and Modified Asphalt  
Solutions**



# Reduce Noise at the Source




**SR 101W ARFC**  
**11/6/03 91 dB(A)**



A Rubberized Asphalt Surface Placed Over Concrete Reduced the Tire Noise by 13 dB(A) in a Quiet Pavement Project in Phoenix, AZ.

**SR 101W PCCP**  
**11/6/03 104 dB(A)**



Rubberized Asphalt has the potential to help agencies reduce noise and the cost of sound walls by reducing the height requirement.

**US 183 – Williamson Co.  
South Bound near San Gabriel  
River**



**Dense Grade  
(Type C)**

**PFC Mix**



Rubberized Asphalt Performs Better,  
Saves Money, and is Sustainable





Contact –

Doug Carlson

Vice President Asphalt Products

Liberty Tire Recycling

1251 Waterfront Place Suite 400

Pittsburgh, PA 15222

602-751-6039

[dcarlson@libertytire.com](mailto:dcarlson@libertytire.com)

